

**10/563903**

**IAP20 Rec'd PCT/PTD 06 JAN 2006**

**ENGLISH TRANSLATION OF ANNEXES TO THE IPER**

1. A polyurethane-polymer hybrid dispersion obtainable by

5

a) preparing a dispersion component or binder component based on an aqueous solution or dispersion of an optionally hydroxy- and/or amino-functional polyurethane-polymer hybrid having fluorinated or unfluorinated side chains, where

10

a<sub>1</sub>) 5 to 100 parts by weight of a laterally fluorine-modified, anionically stabilized polyurethane base dispersion (A) having preferably an ideally linearly segmented structure, a polymer-bonded fluorine content of up to 5% by weight, a hydroxyl number and/or amine number of 0 to 250 mg KOH/g, a solids content of 20% to 60% by weight, a solvent content of 0 to 20% by weight, and an average molar mass of 5000 to 100 000 daltons are admixed with 3 to 300 parts by weight of a monomer component (B) consisting of

15

20

25

(i) 1 to 100 parts by weight of one or more unsaturated monomers (B)(i) having one or more free-radically polymerizable double bonds, selected from the groups of acrylic acid and its derivatives and/or methacrylic acid and its derivatives and/or styrene and its derivatives

30

35

and/or

(ii) 1 to 100 parts by weight of one or more unsaturated fluorine-modified monomers

(B)(ii) having one or more free-radically polymerizable double bonds, selected from the groups of alkyl (per)fluoro (meth)acrylates and/or (per)fluoroalkyl (meth)acrylates and/or (per)fluoroalkyl (per)fluoro(meth)-acrylates and/or reaction products of 1-(1-isocyanato-1-methylethyl)-3-(2-propenyl)benzene (m-TMI) and perfluoroalkyl alcohols

and/or

(iii) 1 to 100 parts by weight of one or more unsaturated optionally fluorine-modified monomers (B)(iii) having one or more free-radically polymerizable double bonds, selected from the group of polyhedral oligomeric polysilsesquioxanes (POSS) of the general formula  $(\text{RSiO}_{1.5})_n$  with  $n = 4, 6, 8, 10, 12$  and R = organic radical having 1 to 100 C atoms and 0 to 50 N and/or 0 to 50 O and/or 0 to 50 F and/or 0 to 50 Si and/or 0 to 50 S atoms and a molar mass of 250 to 25 000 daltons,

with 0.01 to 10 parts by weight of an initiator component (C), consisting of at least one lipophilic free-radical initiator having one or more thermally labile azo or peroxo groups, and 0 to 200 parts by weight of water, it being possible for the monomer component (B), the initiator component (C), and the water to be metered in simultaneously, successively or in a mixture to the polyurethane base dispersion (A), and subsequently

5           a<sub>2</sub>)   in the reaction mixture from stage a<sub>1</sub>), as a  
              result of the thermal decomposition of  
              component (C), carrying out a free-radical  
              polymerization of component (B) within the  
              micelles of the polyurethane base dispersion  
              (A),

10           and, if desired,

15           b)   subsequently reacting the dispersion or  
                  binder component formed from components (A)  
                  to (C) from stage a<sub>2</sub>) with 20 to 100 parts by  
                  weight of a crosslinker component (D) (curing  
                  agent), use being made as crosslinker  
                  component or curing agent (D) of water-  
                  dispersible (paint) polyisocyanates having  
                  aliphatically and/or cycloaliphatically  
                  and/or aromatically attached isocyanate  
20           groups, it being possible for these  
                  polyisocyanates to contain 0 to 25% by weight  
                  of an organic solvent.